

**H T****L T****HIGH TEMPERATURE LIGHT TRANSMISSIBLE THERMOPLASTICS & ADDITIVES****HTLT™ 1070 AA Thermoplastic**

HTLT 1070 AA resin is a transparent, organic/inorganic, amorphous thermoplastic. It is a tough, impact resistant, high-temperature thermoplastic that can be injection molded with precision detail. The HTLT 1070 AA has an index of refraction of 1.55, high visible light transmission and a sustained operating temperature up to 150<sup>0</sup> C. Given its high glass transition temperature, optical lens parts are suitable for use in solder reflow processes including lead-free solder reflow applications up to 285<sup>0</sup> C oven air temperatures. For lead free solder reflow use, consult with a Suncolor representative. The HTLT 1070 AA has been formulated to optimize thermal, photolytic, and hydrolytic oxidation resistance. **HTLT 1070AA is differentiated from other HTLT grades by the incorporation of thermally conductive particles that contribute to uniform stress relief and dimensional stability.**

**PROPERTY\*:**

Specific Gravity, g/cc  
 Melt Temperature, <sup>0</sup>C \*\*  
 Melt Flow @ 330<sup>0</sup>C (626 F), 2.16 kg, (ASTM D 1238)  
 Glass Transition Temperature (<sup>0</sup>C):  
     (<sup>0</sup>C) (DMTA)(2<sup>0</sup>/min. ramp)  
     (<sup>0</sup>C) (DMTA)(4<sup>0</sup>/min. ramp/est.)  
 Mold Shrinkage (%)  
 Coefficient of Linear Thermal Expansion  
 flow/cross flow, ASTM D 696 in/in/<sup>0</sup>F  
 Ball Indentation Hardness (ISO 2039-1)  
 Unnotched Izod Impact (23<sup>0</sup> C, 3.18 mm, ASTM D256)  
 Tensile Elongation @ break, %  
 Tensile Elongation @ yield, %  
 Tensile Modulus (1 mm/min; ASTM 638 lb/in<sup>2</sup>)  
 UL94 Flame Class (UL 94, Class, 1.5 mm thickness)  
 Water Absorption, 24 hour immersion  
 85/85 (85 % r.h & 85<sup>0</sup> C, 1000 hrs.)

**HTLT 1070 AA**

1.12  
 > 300 (572 F)  
 4.0-6.0 (g/10 min.)  
 230<sup>0</sup>  
 265<sup>0</sup>  
 270<sup>0</sup>  
 0.9 – 1.0  
 3.9 E-05  
 115 Mpa  
 No Break (J/m)  
 50.0  
 7.0  
 330,000  
 HB  
 < 0.10 %  
 Pass


**Electrical Properties (23<sup>0</sup> C/50 % r.h.):**

Dissipation Factor, 60 Hz (ASTM D 150) 0.001  
 Tinfoil Electrodes,  
 Volume Resistivity ((ASTM D 257, Ohm\*m) 1.0 E+16  
 Tinfoil Electrodes,  
 Surface Resistivity (ASTM D 257, Ohm) 1.0 E+16  
 Tinfoil Electrodes,  
 Dielectric Constant (ASTM D 150, 60 Hz) 2.9  
 Dielectric Constant (ASTM D 150, 1 MHz) 2.9

\* HTLT 1070 thermoplastics property values are approximate/extrapolated in some cases.

### Typical Optical Properties:

Index of Refraction	1.55
Transmittance (1.0 mm), 585 nm, %	89.0
Luminous Transmittance, Max.Theoretical Value, %	
400 nm	83.0
850 nm	90.0
1000 nm	90.2
Abbe Number	33.5
UV Transmission Cut-Off	360 nm
Haze	2.0-3.0 thickness dependent
Yellowness Index/1000 microns (Clear Transparent Material)	< 1.0



### SUNCOLOR CORPORATION

1325 IRONDALE CIRCLE N. E., NORTH CANTON, OHIO 44720

Tel: (330) 499-7010/ Fax: (330) 499-3692

www.suncolorcorp.com • info@suncolorcorp.com

October 2012 • U.S. Patent No. 8,173,739

International Patents Pending

All information, recommendations, or advice contained in this document and related product data sheets given by Suncolor Corporation whether written or oral is given in good faith, to the best of its knowledge at the time of publication. The products of Suncolor Corporation are sold subject to Conditions of Sale. Nothing in this or any other document shall alter, vary, supersede or operate to waive any of the Conditions of Sale. Each user of the products shall convince himself, through all available sources (including finished product testing in its appropriate environment) of the suitability of the products supplied for its own particular purpose. Because actual use of the products by the user is outside the control of Suncolor Corporation, such use is within the exclusive responsibility of the user. Suncolor Corporation cannot be held responsible for any loss incurred through incorrect or faulty use of the products. Information, recommendations and/or advice are neither made to infringe on any patents, nor to grant a license under any patent or intellectual property right of Suncolor Corporation, nor to grant the right to file for any patent protection.