

SUNCOLOR CORPORATION

ADDITIVES FOR COATINGS, INKS, ADHESIVES & THERMOPLASTICS

SUNSPHERES™ 32.0

DESCRIPTION

SUNSPHERES 32.0 are optically clear, solid fused amorphous silica microspheres specially engineered for paints, liquid and powder coatings, inks, adhesives, thermoplastics and composites. These microspheres increase impact resistance, reduce shrinkage, improve adhesion, and enhance surface qualities such as mar and scratch resistance. The ceramic nature of the product makes composites hard and durable.

The dielectric properties and very high electrical receptivity of these materials over a wide range of temperatures, together with their low thermal conductivity, allow their use as an electrical and thermal insulating material in a range of environments. SUNSPHERES 32.0 are inert to most substances, including virtually all acids, allowing their use in arduous and hostile environments.

LIGHT TRANSMISSION

The Sunospheres 32.0 efficiently transmit ultraviolet and visible light from 200 nanometers through the visible spectrum. These microspheres space pigments and promote efficient, thorough curing by ultraviolet radiation.

SIZING & USE;

SUNSPHERES 32.0 have a median particle size of 32 microns with 95% of particles passing 65 microns. Recommended dosages range from 3 to 50% by total weight of formulation. SUNSPHERES 32.0 are designed for use in thick coatings appropriate to their size. The SUNSPHERES 32.0 provide texture in thinner coatings. Due to their low surface area, Sunospheres 32.0 are easily dispersed.

TYPICAL PARTICLE SIZE ANALYSIS:			PHYSICAL & CHEMICAL PROPERTIES:	
By MicroTrac/ Median Diameter Approx. 32.0Microns				
(Microns) 65	(% Passing)	95	Index of Refraction	1.458(n _D)
45		71	Softening Temperature	>1000 ⁰ C
22		35	Strain Point	>600 ⁰ C
11		14	Coefficient of Thermal Expansion	55 x 10 ⁻⁷ / ⁰ C
5.5		6	DC Resistivity	1 x 10 ⁸
2.75		3.5	Hardness (Mohs) Scale	7.0
10% Finer		8.5	BET Surface Area (sq.m/g)	0.3
50% Finer		31	Ph	5-6
95% Finer		65	Structure/Amorphous SiO ₂	>99%
Shape: Spherical to Semi-Spherical/Solid Microspheres			Crushing Strength	>60,000 psi

THE MARKS SUNSPHERES™ ARE PROPRIETARY TRADEMARKS OF SUNCOLOR CORPORATION. UVT LIGHT TRANSMISSION TECHNOLOGY IS THE SUBJECT OF US & INTERNATIONAL PATENTS PENDING AND COVERED UNDER US PATENT NO. 6,350,792 & NO. 6,660,374. THE INFORMATION PRESENTED IS TO THE BEST OF OUR KNOWLEDGE TRUE AND CORRECT. ALL SUGGESTIONS AND RECOMMENDATIONS ARE WITHOUT WARRANTY AND GUARANTEE AS THE CONDITIONS OF USE ARE BEYOND OUR CONTROL. WE DISCLAIM ANY LIABILITY INCURRED IN CONNECTION WITH THE USE OF THESE DATA. Rev. January, 2015.

See reverse side for additional information

SUNCOLOR CORPORATION

1325 IRONDALE CIRCLE N.E.

NORTH CANTON, OHIO 44720

DIRECT TELEPHONE: (330) 499-7010 FAX: (330) 499-3692

FOR SAMPLES & CUSTOMER SERVICE, CONTACT MARY ZINK

TEL: 330.327.2997 or mzink@suncolorcorp.com

All information, recommendations, or advice contained in this document and related product data sheets given by Suncolor Corporation whether written or oral is given in good faith, to the best of its knowledge at the time of publication. The products of Suncolor Corporation are sold subject to Conditions of Sale. Nothing in this or any other document shall alter, vary, supersede or operate to waive any of the Conditions of Sale. Each user of the products shall convince himself, through all available sources (including finished product testing in its appropriate environment) of the suitability of the products supplied for its own particular purpose. Because actual use of the products by the user is outside the control of Suncolor Corporation, such use is within the exclusive responsibility of the user. Suncolor Corporation cannot be held responsible for any loss incurred through incorrect or faulty use of the products. Information, recommendations and/or advice are neither made to infringe on any patents, nor to grant a license under any patent or intellectual property right of Suncolor Corporation, nor to grant the right to file for any patent protection.